



TEST REPORT

Page 1 of 2

ULR - TC652820000000006F

Report No.:2002060010

Date: 08-02-2020

Issued To:

M/s GUPTA SHUTTERING HOUSE

PLOT NO. - 58-59, PHASE - VI, GURGAON

SISTER CONCERN

: - KARNAVATI SHUTTERING HOUSE (AHMDABAD)

: - AMIT SHUTTERING STORE (GURGAON)

: - SUMIT SHUTTERING STORE (GURGAON)

Sample Description : MS PIPE 60 OD FOR USE ADJUSTABLE OUTER AND INNER
Sample Received Date : 06-02-2020
Sample Drawn By : Client
Specification : --
Test Requested : TENSILE
Test Method : Refer to Attached Pages.
Test Result : Refer to Attached Pages.

Authentication: To Check authenticity of Test report (s), Scan QR code to get original data.



Terms & Conditions:

1. Sample will not be retained more than one month for chemical and three month for mechanical unless specified instructed. 2. Samples analysis conducted on as received basis and followed by customer description, unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. The Test marked with an * are not accredited by NABL. 5. Any Complaints matter about this report should be communicated in written, within 7 days of issue of this report. 6. The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 7. Total liability of our laboratory is limited to the invoiced amount only. 8. This report cannot be used as and evidence in a court of law without the written approval of the laboratory.

MSF 5.10.01

Govt. Approved Laboratory

ISO 9001 : 2015, ISO 14001:2015 & OHSAS 18001:2007 Certified Laboratory





TEST REPORT

Page 2 of 2

ULR - TC652820000000006F

Report No.:2002060010

Date: 08-02-2020

I. Mechanical

1. Mechanical Properties of Metals

TENSILE TEST

Test performed on : 06-02-2020 to 08-02-2020

Test Method : IS 1608 ,Part-1:2018

Test Parameter Result Requirement Conformity

(as per IS:1161:1998,

Gr.-Yst240)

Tensile strength (N/mm ²)	501.20	410.0 min.	Yes
Yield strength (N/mm ²)	345.50	240.0 min.	Yes
Elongation (%)	22.30	17.0 min.	Yes

Remarks: Sample conforms to IS:1161:1998,Gr.- Yst240 with respect to above test.

-----End of Report-----



Souvik

souvik

TECHNICAL MANAGER

Authorised Signatory

Authentication: To Check authenticity of Test report (s), Scan QR code to get original data.



Terms & Conditions:

Govt. Approved Laboratory
ISO 9001 : 2015, ISO 14001:2015 & OHSAS 18001:2007 Certified Laboratory

1. Sample will not be retained more than one month for chemical and three month for mechanical unless specified instructed. 2. Samples analysis conducted on as received basis and followed by customer description, unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. The Test marked with an * are not accredited by NABL. 5. Any Complaints matter about this report should be communicated in written, within 7 days of issue of this report. 6. The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 7. Total liability of our laboratory is limited to the invoiced amount only. 8. This report cannot be used as and evidence in a court of law without the written approval of the laboratory.

MSF 5.10.01

